

English Version

Welding consumables - Tubular cored electrodes and rods for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels - Classification (ISO 17633:2017)

Produits consommables pour le soudage - Fils et baguettes fourrés pour le soudage à l'arc avec ou sans protection gazeuse des aciers inoxydables et des aciers résistant aux températures élevées - Classification (ISO 17633:2017)

Schweißzusätze - Fülldrahtelektroden und Füllstäbe zum Metall-Lichtbogenschweißen mit und ohne Gasschutz von nichtrostenden und hitzebeständigen Stählen - Einteilung (ISO 17633:2017)

This European Standard was approved by CEN on 17 November 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 17633:2018) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2018, and conflicting national standards shall be withdrawn at the latest by July 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17633:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17633:2017 has been approved by CEN as EN ISO 17633:2018 without any modification.

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
5 Symbols and requirements	2
5.1 General	2
5.2 Symbol for the product	3
5.3 Symbol for the chemical composition of all-weld metal	3
5.4 Symbol for type of core	19
5.5 Symbol for shielding gas	19
5.6 Symbol for welding position	20
6 Mechanical test	20
6.1 Preheating and interpass temperatures	20
6.2 Pass sequence	21
7 Chemical analysis	21
8 Rounding procedure	21
9 Retests	22
10 Technical delivery conditions	22
11 Examples of designation	22
Annex A (informative) Comparison charts of alloy designation according to nominal composition and alloy type	24
Annex B (informative) Description of types of core — Classification according to nominal composition	26
Annex C (informative) Description of types of tubular cored electrodes and rods — Classification according to alloy type	27
Annex D (informative) Considerations on weld metal ferrite contents	28
Bibliography	31

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 17633:2010), which has been technically revised and contains the following changes:

- the chemical compositions and mechanical properties for a number of alloy designations have been updated;
- new alloy designations have been added;
- a limitation on Bi has been added to the footnotes of Tables 1B-1, 1B-2, 1B-3 and 1B-4;
- the requirements for fillet weld testing have been removed following the same change in ISO 18276;
- the wording in clauses on chemical analysis, rounding procedure and retests has been updated;
- clarification has been brought when a product covers both electrodes and rods;
- additional examples for designations have been inserted.

Requests for official interpretations of any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This document provides a classification system for tubular cored electrodes and rods for welding stainless and heat resisting steels. It recognizes that there are two somewhat different approaches in the global market to classifying a given tubular stainless steel welding consumable, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both, where suitable) identifies a product as classified in accordance with this document. The classification in accordance with system A was mainly based on EN 12073:1999. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

Welding consumables — Tubular cored electrodes and rods for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels — Classification

1 Scope

This document specifies requirements for classification of tubular flux and metal cored electrodes and rods, based on the all-weld metal chemical composition, the type of core, shielding gas, welding position and the all-weld metal mechanical properties, in the as-welded or heat-treated conditions, for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels.

This document is a combined standard providing for classification utilizing a system based upon nominal composition or utilizing a system based upon alloy type.

- a) Clauses, subclauses, and tables which carry the suffix letter "A" are applicable only to products classified using the system based upon nominal composition.
- b) Clauses, subclauses, and tables which carry the suffix letter "B" are applicable only to products classified using the system based upon alloy type.
- c) Clauses, subclauses, and tables which do not have either the suffix letter "A" or the suffix letter "B" are applicable to all products classified in accordance with this document.

This document does not use pulsed current for determining the product classification.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947, *Welding and allied processes — Welding positions*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*. Amended by ISO 15792-1:2000/Amd 1:2011.

ISO 80000-1:2009, *Quantities and units — Part 1: General*. Corrected by ISO 80000-1:2009/Cor 1:2011.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Classification

Classification designations are based upon two approaches to indicate the chemical composition of the all-weld metal deposit obtained with a given electrode or rod.

The “nominal composition” approach uses designation components indicating directly the nominal levels of certain alloying elements, given in a particular order, and some symbols for low but significant levels of other elements, whose levels are not conveniently expressed as integers. The “alloy type” approach uses tradition-based three- or four-digit designations for alloy families, and an occasional additional character or characters for compositional modifications of each original alloy within the family.

This clause includes the symbols for the type of product, the chemical composition of all-weld metal, the type of core, the shielding gas and the welding position, in accordance with the symbols defined in [Clause 5](#).

In most cases, a given commercial product can be classified in both systems. Then either or both classification designations can be used for the product.

4A Classification according to nominal composition

The classification is divided into five parts:

- a) the first part gives a symbol indicating the product to be identified (see [5.2A](#));
- b) the second part gives a symbol indicating the chemical composition of the all-weld metal (see [Table 1A](#));
- c) the third part gives a symbol indicating the type of core (see [Table 3A](#));
- d) the fourth part gives a symbol indicating the shielding gas (see [5.5](#));
- e) the fifth part gives a symbol indicating the welding position (see [Table 4A](#)).

4B Classification according to alloy type

The classification is divided into five parts:

- a) the first part gives a symbol indicating the tubular cored electrode and rod (see [5.2B](#));
- b) the second part gives a symbol indicating the chemical composition of the all-weld metal (see [Table 1B-1](#) to [Table 1B-4](#));
- c) the third part gives a symbol indicating the type of core (see [Table 3B](#));
- d) the fourth part gives a symbol indicating the shielding gas (see [5.5](#));
- e) the fifth part gives a symbol indicating the welding position (see [Table 4B](#)).

The full identification (see [Clause 11](#)) shall be used on packages and in the manufacturer’s literature and data sheets.

5 Symbols and requirements

5.1 General

A given tubular cored electrode may be classified with more than one shielding gas. In such cases, each shielding gas results in a separate classification.

5.2 Symbol for the product

5.2A Classification according to nominal composition

The symbol for tubular cored product used in the metal arc welding process shall be the letter "T".

5.2B Classification according to alloy type

The symbol for tubular cored product used in the metal arc welding process shall be the letters "TS". The initial letter, "T", indicates tubular cored electrode or rod as distinguished from covered electrodes and from solid electrodes and rods. The second letter, "S", indicates that the alloy system is stainless or heat-resisting steel.

5.3 Symbol for the chemical composition of all-weld metal

5.3A Classification according to nominal composition

The symbols in [Table 1A](#) identify the chemical composition of all-weld metal determined in accordance with [Clause 7](#).

The all-weld metal obtained with the tubular cored product in [Table 1A](#) under conditions given in [Clause 6](#) shall also fulfil the requirements given in [Table 2A](#). (See [Annex A](#).)

5.3B Classification according to alloy type

The symbols in [Table 1B-1](#) identify the chemical composition of all-weld metal for gas shielded flux cored electrodes determined in accordance with [Clause 7](#).

The symbols in [Table 1B-2](#) identify the chemical composition of all-weld metal for non-gas shielded flux cored electrodes determined in accordance with [Clause 7](#).

The symbols in [Table 1B-3](#) identify the chemical composition of all-weld metal for gas shielded metal cored electrodes determined in accordance with [Clause 7](#).

The symbols in [Table 1B-4](#) identify the chemical composition of all-weld metal for cored products for gas tungsten arc welding determined in accordance with [Clause 7](#).

The all-weld metal obtained with the tubular cored electrodes and rods in [Table 1B-1](#), [Table 1B-2](#), [Table 1B-3](#) and [Table 1B-4](#) under conditions given in [Clause 6](#) shall also fulfil the requirements given in [Table 2B](#). (See [Annex A](#).)

**Table 1A — Symbols and all-weld metal chemical composition requirements
(classification according to nominal composition)**

Alloy designation according to nominal composition	Chemical composition, % (by mass) ^{a,b}											
	C	Mn	Si	P ^c	S ^c	Cr	Ni	Mo	Nb + Ta ^d	Cu	N	Others
Martensitic/ferritic types												
13	0,12	1,5	1,0	0,030	0,025	11,0 to 14,0	0,3	0,3	—	0,5	—	—
13 Ti	0,10	0,80	1,0	0,030	0,030	10,5 to 13,0	0,3	0,3	—	0,5	—	Ti: 10 × C to 1,5
13 4	0,06	1,5	1,0	0,030	0,025	11,0 to 14,5	3,0 to 5,0	0,4 to 1,0	—	0,5	—	—
17	0,12	1,5	1,0	0,030	0,025	16,0 to 18,0	0,3	0,3	—	0,5	—	—
Austenitic types												
19 9 L	0,04	2,0	1,2	0,030	0,025	18,0 to 21,0	9,0 to 11,0	0,3	—	0,5	—	—
19 9 Nb	0,08	2,0	1,2	0,030	0,025	18,0 to 21,0	9,0 to 11,0	0,3	8 × C to 1,1	0,5	—	—
19 12 3 L	0,04	2,0	1,2	0,030	0,025	17,0 to 20,0	10,0 to 13,0	2,5 to 3,0	—	0,5	—	—
19 12 3 Nb	0,08	2,0	1,2	0,030	0,025	17,0 to 20,0	10,0 to 13,0	2,5 to 3,0	8 × C to 1,1	0,5	—	—
Ferritic-austenitic types (sometimes referred to as austenitic-ferritic types)												
22 9 3 N L	0,04	2,5	1,2	0,030	0,025	21,0 to 24,0	7,5 to 10,5	2,5 to 4,0	—	0,5	0,08 to 0,20	—
23 7 N L	0,04	0,4 to 1,5	1,0	0,030	0,020	22,5 to 25,5	6,5 to 10,0	0,8	—	0,5	0,10 to 0,20	—
25 9 4 N L	0,04	2,5	1,2	0,030	0,025	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	—	—	0,20 to 0,30	—
25 9 4 Cu N L	0,04	2,5	1,2	0,030	0,025	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	—	1,0 to 2,5	0,20 to 0,30	—
Fully austenitic types												
18 16 5 N L ^e	0,03	1,0 to 4,0	1,0	0,03	0,02	17,0 to 20,0	16,0 to 19,0	3,5 to 5,0	—	0,5	0,10 to 0,20	—
19 13 4 N L ^e	0,04	1,0 to 5,0	1,2	0,030	0,025	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	—	0,5	0,08 to 0,20	—
20 25 5 Cu N L ^e	0,03	1,0 to 4,0	1,0	0,03	0,02	19,0 to 22,0	24,0 to 27,0	4,0 to 6,0	—	1,0 to 2,0	0,10 to 0,20	—
Special types — Often used for dissimilar metal joining												
18 8 Mn	0,20	4,5 to 7,5	1,2	0,035	0,025	17,0 to 20,0	7,0 to 10,0	0,3	—	0,5	—	—
18 9 Mn Mo	0,04 to 0,14	3,0 to 5,0	1,2	0,035	0,025	18,0 to 21,5	9,0 to 11,0	0,5 to 1,5	—	—	—	—
20 10 3	0,08	2,5	1,2	0,035	0,025	19,5 to 22,0	9,0 to 11,0	2,0 to 4,0	—	0,5	—	—
23 12 L	0,04	2,5	1,2	0,030	0,025	22,0 to 25,0	11,0 to 14,0	0,3	—	0,5	—	—

Table 1A (continued)

Alloy designation according to nominal composition	Chemical composition, % (by mass) ^{a,b}											
	C	Mn	Si	P _c	S _c	Cr	Ni	Mo	Nb + Ta ^d	Cu	N	Others
23 12 Nb	0,08	1,0 to 2,5	1,0	0,03	0,02	22,0 to 25,0	11,0 to 14,0	0,3	10 × C to 1,0	0,5	—	—
23 12 2 L	0,04	2,5	1,2	0,030	0,025	22,0 to 25,0	11,0 to 14,0	2,0 to 3,0	—	0,5	—	—
29 9	0,15	2,5	1,2	0,035	0,025	27,0 to 31,0	8,0 to 12,0	0,3	—	0,5	—	—
Heat-resisting types												
16 8 2	0,10	1,0	1,0 to 2,5	0,03	0,02	14,5 to 17,5	7,5 to 9,5	1,0 to 2,5	—	0,5	—	Cr + Mo: 18,5
19 9 H	0,04 to 0,08	1,0	1,0 to 2,5	0,03	0,02	18,0 to 21,0	9,0 to 11,0	0,3	—	0,5	—	—
21 10 N	0,06 to 0,09	0,3 to 1,0	1,0 to 2,0	0,02	0,01	20,5 to 22,5	9,5 to 11,0	0,5	—	0,5	0,10 to 0,20	Ce: 0,05
22 12 H	0,15	2,5	1,2	0,030	0,025	20,0 to 23,0	10,0 to 13,0	0,3	—	0,5	—	—
25 4	0,15	2,0	1,0 to 2,5	0,03	0,02	24,0 to 27,0	4,0 to 6,0	0,3	—	0,5	—	—
25 20 ^e	0,06 to 0,20	1,0 to 5,0	1,2	0,030	0,025	23,0 to 27,0	18,0 to 22,0	0,3	—	0,5	—	—
Z ^f	Any other agreed composition											
<p>^a Single values are maximum values.</p> <p>^b "No requirement for analysis" is indicated by a dash.</p> <p>^c The sum of P and S shall not exceed 0,050 % (by mass), except for 18 16 5 N L, 18 8 Mn, and 29 9.</p> <p>^d Up to 20 % (by mass) of the amount of Nb can be replaced by Ta.</p> <p>^e The all-weld metal is in most cases fully austenitic and therefore can be susceptible to microfissuring or hot cracking. The occurrence of fissuring or cracking is reduced by increasing the weld metal manganese level and in recognition of this the manganese range is extended for a number of grades.</p> <p>^f Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and it is possible that two products with the same Z classification are not interchangeable.</p>												

Table 1B — -1 — Symbols and all-weld metal chemical composition requirements of gas shielded flux cored electrodes
(classification according to alloy type)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
307	C1, M12, M21, Z	0,13	3,30 to 4,75	1,0	0,04	0,03	18,0 to 20,5	9,0 to 10,5	0,5 to 1,5	—	0,75	—	—
308	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	—	0,75	—	—
308L	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 12,0	0,75	—	0,75	—	—
308H	C1, M12, M21, Z	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	—	0,75	—	—
308Mo	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	2,0 to 3,0	—	0,75	—	—
308LMo	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
308N	C1, M12, M21, Z	0,10	1,0 to 4,0	1,0	0,04	0,03	20,0 to 25,0	7,0 to 11,0	0,5	—	0,5	0,12 to 0,30	—
309	C1, M12, M21, Z	0,10	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309L	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309H	C1, M12, M21, Z	0,04 to 0,10	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309Mo	C1, M12, M21, Z	0,12	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	—	0,75	—	—
309LMo	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	—	0,75	—	—
309LNb	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,75	0,70 to 1,00	0,75	—	—
309LNiMo	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	20,5 to 23,5	15,0 to 17,0	2,5 to 3,5	—	0,75	—	—
310	C1, M12, M21, Z	0,20	1,0 to 2,5	1,0	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
312	C1, M12, M21, Z	0,15	0,5 to 2,5	1,0	0,04	0,03	28,0 to 32,0	8,0 to 10,5	0,75	—	0,75	—	—
316	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316L	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316H	C1, M12, M21, Z	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316LCu	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 16,0	1,25 to 2,75	—	1,0 to 2,5	—	—
317	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	12,0 to 14,0	3,0 to 4,0	—	0,75	—	—
317L	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	12,0 to 14,0	3,0 to 4,0	—	0,75	—	—
318	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	8 × C to 1,0	0,75	—	—
347	C1, M12, M21, Z	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—
347L	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—
347H	C1, M12, M21, Z	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—
409	C1, M12, M21, Z	0,10	0,80	1,0	0,04	0,03	10,5 to 13,5	0,60	0,75	—	0,75	—	Ti: 10 × C to 1,5
409Nb	C1, M12, M21, Z	0,10	1,2	1,0	0,04	0,03	10,5 to 13,5	0,6	0,5	8 × C to 1,5	0,5	—	—
410	C1, M12, M21, Z	0,12	1,2	1,0	0,04	0,03	11,0 to 13,5	0,60	0,75	—	0,75	—	—
410NiMo	C1, M12, M21, Z	0,06	1,0	1,0	0,04	0,03	11,0 to 12,5	4,0 to 5,0	0,40 to 0,70	—	0,75	—	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
430	C1, M12, M21, Z	0,10	1,2	1,0	0,04	0,03	15,0 to 18,0	0,60	0,75	—	0,75	—	—
430Nb	C1, M12, M21, Z	0,10	1,2	1,0	0,04	0,03	15,0 to 18,0	0,6	0,5	0,5 to 1,5	0,5	—	—
16-8-2	C1, M12, M21, Z	0,10	0,5 to 2,5	0,75	0,04	0,03	14,5 to 17,5	7,5 to 9,5	1,0 to 2,0	—	0,75	—	Cr + Mo: 18,5
2209	C1, M12, M21, Z	0,04	0,5 to 2,0	1,0	0,04	0,03	21,0 to 24,0	7,5 to 10,0	2,5 to 4,0	—	0,75	0,08 to 0,20	—
2307	C1, M12, M21, Z	0,04	2,0	1,0	0,03	0,02	22,5 to 25,5	6,5 to 10,0	0,8	—	0,50	0,10 to 0,20	—
2553	C1, M12, M21, Z	0,04	0,5 to 1,5	0,75	0,04	0,03	24,0 to 27,0	8,5 to 10,5	2,9 to 3,9	—	1,5 to 2,5	0,10 to 0,25	—
2594	C1, M12, M21, Z	0,04	0,5 to 2,5	1,0	0,04	0,03	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	—	1,5	0,20 to 0,30	W: 1,0
2594W	C1, M12, M21, Z	0,04	0,5 to 2,0	1,0	0,04	0,03	23,0 to 27,0	8,0 to 11,0	2,5 to 4,0	—	1,0	0,08 to 0,30	W: 1,0 to 2,5
Z ^d	C1, M12, M21, Z	Any other agreed composition											

^a Single values are maximum values.

^b "No requirement for analysis" is indicated by a dash.

^c For alloys intended for high temperature, Bi should be restricted to 20 ppm maximum.

^d Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

Table 1B — -2 — Symbols and all-weld metal chemical composition requirements of non-gas shielded flux cored electrodes
(classification according to alloy type)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
307	NO	0,13	3,30 to 4,75	1,0	0,04	0,03	19,5 to 22,0	9,0 to 10,5	0,5 to 1,5	—	0,75	—	—
308	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308L	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	19,5 to 22,0	9,0 to 12,0	0,75	—	0,75	—	—
308H	NO	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308Mo	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	2,0 to 3,0	—	0,75	—	—
308LMo	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
308HMo	NO	0,07 to 0,12	1,25 to 2,25	0,25 to 0,80	0,04	0,03	19,0 to 21,5	9,0 to 10,7	1,8 to 2,4	—	0,75	—	—
309	NO	0,10	0,5 to 2,5	1,0	0,04	0,03	23,0 to 25,5	12,0 to 14,0	0,75	—	0,75	—	—
309L	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	23,0 to 25,5	12,0 to 14,0	0,75	—	0,75	—	—
309Mo	NO	0,12	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	—	0,75	—	—
309LMo	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	—	0,75	—	—
309LNb	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	23,0 to 25,5	12,0 to 14,0	0,75	0,70 to 1,00	0,75	—	—
310	NO	0,20	1,0 to 2,5	1,0	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
312	NO	0,15	0,5 to 2,5	1,0	0,04	0,03	28,0 to 32,0	8,0 to 10,5	0,75	—	0,75	—	—
316	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 20,5	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316L	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 20,5	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316LK	NO	0,04	0,5 to 2,5	1,0	0,04	0,3	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316H	NO	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 20,5	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316LCu	NO	0,03	0,5 to 2,5	1,0	0,04	0,03	18,0 to 20,5	11,0 to 16,0	1,25 to 2,75	—	1,0 to 2,5	—	—
317	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	18,5 to 21,0	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
317L	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	18,5 to 21,0	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
318	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 20,5	11,0 to 14,0	2,0 to 3,0	8 × C to 1,0	0,75	—	—
347	NO	0,08	0,5 to 2,5	1,0	0,04	0,03	19,0 to 21,5	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
347L	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	19,0 to 21,5	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—
409	NO	0,10	0,80	1,0	0,04	0,03	10,5 to 13,5	0,60	0,75	—	0,75	—	Ti: 10 × C to 1,5
409Nb	NO	0,12	1,0	1,0	0,04	0,03	10,5 to 14,0	0,6	0,75	8 × C to 1,5	0,75	—	—
410	NO	0,12	1,0	1,0	0,04	0,03	11,0 to 13,5	0,60	0,75	—	0,75	—	—
410NiMo	NO	0,06	1,0	1,0	0,04	0,03	11,0 to 12,5	4,0 to 5,0	0,40 to 0,70	—	0,75	—	—
430	NO	0,10	1,0	1,0	0,04	0,03	15,0 to 18,0	0,60	0,75	—	0,75	—	—
430Nb	NO	0,10	1,0	1,0	0,04	0,03	15,0 to 18,0	0,6	0,75	0,5 to 1,5	0,75	—	—
16-8-2	NO	0,10	0,5 to 2,5	0,75	0,04	0,03	14,5 to 17,5	7,5 to 9,5	1,0 to 2,0	—	0,75	—	Cr + Mo: 18,5
2209	NO	0,04	0,5 to 2,0	1,0	0,04	0,03	21,0 to 24,0	7,5 to 10,0	2,5 to 4,0	—	0,75	0,08 to 0,20	—
2307	NO	0,04	2,0	1,0	0,03	0,02	22,5 to 25,5	6,5 to 10,0	0,8	—	0,50	0,10 to 0,20	—
2553	NO	0,04	0,5 to 1,5	0,75	0,04	0,03	24,0 to 27,0	8,5 to 10,5	2,9 to 3,9	—	1,5 to 2,5	0,10 to 0,25	—
2594	NO	0,04	0,5 to 2,5	1,0	0,04	0,03	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	—	1,5	0,20 to 0,30	W: 1,0
Z ^d	NO	Any other agreed composition											

^a Single values are maximum values.

^b "No requirement for analysis" is indicated by a dash.

^c For alloys intended for high temperature, Bi should be restricted to 20 ppm maximum.

^d Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

**Table 1B — 3 — Symbols and all-weld metal chemical composition requirements of gas shielded metal cored electrodes
(classification according to alloy type)**

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											Others ^c
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	
209	M12, M13, M21, I1, Z	0,05	4,0 to 7,0	0,90	0,03	0,03	20,5 to 24,0	9,5 to 12,0	1,5 to 3,0	—	0,75	0,10 to 0,30	V: 0,10 to 0,30
218	M12, M13, M21, I1, Z	0,10	7,0 to 9,0	3,5 to 4,5	0,03	0,03	16,0 to 18,0	8,0 to 9,0	0,75	—	0,75	0,08 to 0,18	—
219	M12, M13, M21, I1, Z	0,05	8,0 to 10,0	1,00	0,03	0,03	19,0 to 21,5	5,5 to 7,0	0,75	—	0,75	0,10 to 0,30	—
240	M12, M13, M21, I1, Z	0,05	10,5 to 13,5	1,00	0,03	0,03	17,0 to 19,0	4,0 to 6,0	0,75	—	0,75	0,10 to 0,30	—
307	M12, M13, M21, I1, Z	0,04 to 0,14	3,30 to 4,75	0,30 to 0,65	0,03	0,03	19,5 to 22,0	8,0 to 10,7	0,5 to 1,5	—	0,75	—	—
308	M12, M13, M21, I1, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308Si	M12, M13, M21, I1, Z	0,08	1,0 to 2,5	0,65 to 1,00	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308H	M12, M13, M21, I1, Z	0,04 to 0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,50	—	0,75	—	—
308L	M12, M13, M21, I1, Z	0,03	1,0 to 2,5	0,30 to 0,65	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308LSi	M12, M13, M21, I1, Z	0,03	1,0 to 2,5	0,65 to 1,00	0,03	0,03	19,5 to 22,0	9,0 to 11,0	0,75	—	0,75	—	—
308LMo	M12, M13, M21, I1, Z	0,04	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
308Mo	M12, M13, M21, I1, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	—	0,75	—	—
309	M12, M13, M21, I1, Z	0,12	1,0 to 2,5	0,30 to 0,65	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309L	M12, M13, M21, I1, Z	0,03	1,0 to 2,5	0,30 to 0,65	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309LSi	M12, M13, M21, I1, Z	0,03	1,0 to 2,5	0,65 to 1,00	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
309Si	M12, M13, M21, 11, Z	0,12	1,0 to 2,5	0,65 to 1,00	0,03	0,03	23,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
309LMo	M12, M13, M21, 11, Z	0,03	1,0 to 2,5	0,30 to 0,65	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—
309Mo	M12, M13, M21, 11, Z	0,12	1,0 to 2,5	0,30 to 0,65	0,03	0,03	23,0 to 25,0	12,0 to 14,0	2,0 to 3,0	—	0,75	—	—
310	M12, M13, M21, 11, Z	0,08 to 0,15	1,0 to 2,5	0,30 to 0,65	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,75	—	0,75	—	—
312	M12, M13, M21, 11, Z	0,15	1,0 to 2,5	0,30 to 0,65	0,03	0,03	28,0 to 32,0	8,0 to 10,5	0,75	—	0,75	—	—
316	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316H	M12, M13, M21, 11, Z	0,04 to 0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316L	M12, M13, M21, 11, Z	0,03	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316LMn	M12, M13, M21, 11, Z	0,03	5,0 to 9,0	0,30 to 0,65	0,03	0,03	19,0 to 22,0	15,0 to 18,0	2,5 to 3,5	—	0,75	0,10 to 0,20	—
316LSi	M12, M13, M21, 11, Z	0,03	1,0 to 2,5	0,65 to 1,00	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
316Si	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,65 to 1,00	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
317	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
317L	M12, M13, M21, 11, Z	0,03	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,5 to 20,5	13,0 to 15,0	3,0 to 4,0	—	0,75	—	—
318	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,0 to 20,0	11,0 to 14,0	2,0 to 3,0	8 × C, to 1,0	0,75	—	—
320	M12, M13, M21, 11, Z	0,07	2,5	0,60	0,03	0,03	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	8 × C to 1,0	3,0 to 4,0	—	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
320LR	M12, M13, M21, 11, Z	0,025	1,5 to 2,0	0,15	0,015	0,02	19,0 to 21,0	32,0 to 36,0	2,0 to 3,0	8 × C to 0,40	3,0 to 4,0	—	—
321	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	18,5 to 20,5	9,0 to 10,5	0,75	—	0,75	—	Ti: 9 × C to 1,0
330	M12, M13, M21, 11, Z	0,18 to 0,25	1,0 to 2,5	0,30 to 0,65	0,03	0,03	15,0 to 17,0	34,0 to 37,0	0,75	—	0,75	—	—
347	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,30 to 0,65	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	10 × C to 1,0	0,75	—	—
347Si	M12, M13, M21, 11, Z	0,08	1,0 to 2,5	0,65 to 1,00	0,03	0,03	19,0 to 21,5	9,0 to 11,0	0,75	10 × C to 1,0	0,75	—	—
383	M12, M13, M21, 11, Z	0,025	1,0 to 2,5	0,50	0,02	0,03	26,5 to 28,5	30,0 to 33,0	3,2 to 4,2	—	0,70 to 1,50	—	—
385	M12, M13, M21, 11, Z	0,025	1,0 to 2,5	0,50	0,02	0,03	19,5 to 21,5	24,0 to 26,0	4,2 to 5,2	—	1,2 to 2,0	—	—
409	M12, M13, M21, 11, Z	0,08	0,8	0,8	0,03	0,03	10,5 to 13,5	0,6	0,50	—	0,75	—	Ti: 10 × C to 1,5
409Nb	M12, M13, M21, 11, Z	0,08	0,8	1,0	0,04	0,03	10,5 to 13,5	0,6	0,50	10 × C to 0,75	0,75	—	—
410	M12, M13, M21, 11, Z	0,12	0,6	0,5	0,03	0,03	11,5 to 13,5	0,6	0,75	—	0,75	—	—
410NiMo	M12, M13, M21, 11, Z	0,06	0,6	0,5	0,03	0,03	11,0 to 12,5	4,0 to 5,0	0,4 to 0,7	—	0,75	—	—
420	M12, M13, M21, 11, Z	0,25 to 0,40	0,6	0,5	0,03	0,03	12,0 to 14,0	0,6	0,75	—	0,75	—	—
430	M12, M13, M21, 11, Z	0,10	0,6	0,5	0,03	0,03	15,5 to 17,0	0,6	0,75	—	0,75	—	—
430Nb	M12, M13, M21, 11, Z	0,10	1,2	1,0	0,04	0,03	15,0 to 18,0	0,6	0,75	0,5 to 1,5	0,75	—	—
439	M12, M13, M21, 11, Z	0,04	0,8	0,8	0,03	0,03	17,0 to 19,0	0,6	0,5	—	0,75	—	Ti: 10 × C to 1,1

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
439Nb	M12, M13, M21, I1, Z	0,04	0,8	0,8	0,03	0,03	17,0 to 20,0	0,6	0,5	8 × C to 0,75	0,75	—	Ti: 0,10 to 0,75
446LMo	M12, M13, I1, Z	0,015	0,4	0,4	0,02	0,02	25,0 to 27,5	0,5	0,75 to 1,50	—	0,5	0,015	Ni + Cu = 0,5
630	M12, M13, M21, I1, Z	0,05	0,25 to 0,75	0,75	0,03	0,03	16,00 to 16,75	4,5 to 5,0	0,75	0,15 to 0,30	3,25 to 4,00	—	—
2209	M12, M13, M21, I1, Z	0,03	0,50 to 2,00	0,90	0,03	0,03	21,5 to 23,5	7,5 to 9,5	2,5 to 3,5	—	0,75	0,08 to 0,20	—
2553	M12, M13, M21, I1, Z	0,04	1,5	1,0	0,04	0,03	24,0 to 27,0	4,5 to 6,5	2,9 to 3,9	—	1,5 to 2,5	0,10 to 0,25	—
2594	M12, M13, M21, I1, Z	0,03	2,5	1,0	0,03	0,02	24,0 to 27,0	8,0 to 10,5	2,5 to 4,5	—	1,5	0,20 to 0,30	W: 1,0
16-8-2	M12, M13, M21, I1, Z	0,10	1,0 to 2,0	0,30 to 0,65	0,03	0,03	14,5 to 16,5	7,5 to 9,5	1,0 to 2,0	—	0,75	—	—
19-10H	M12, M13, M21, I1, Z	0,04 to 0,08	1,0 to 2,0	0,30 to 0,65	0,03	0,03	18,5 to 20,0	9,0 to 11,0	0,25	0,05	0,75	—	Ti: 0,05
33-31	M12, M13, M21, I1, Z	0,015	2,00	0,50	0,02	0,01	31,0 to 35,0	30,0 to 33,0	0,5 to 2,0	—	0,3 to 1,2	0,35 to 0,60	—

Table 1B (continued)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											Others ^c
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	
3556	M12, M13, M21, I1, Z	0,05 to 0,15	0,50 to 2,00	0,20 to 0,80	0,04	0,015	21,0 to 23,0	19,0 to 22,5	2,5 to 4,0	—	—	0,10 to 0,30	Co: 16,0 to 21,0 W: 2,0 to 3,5 Nb: 0,30 Ta: 0,30 to 1,25 Al: 0,10 to 0,50 Zr: 0,001 to 0,100 La: 0,005 to 0,100 B: 0,02
Z ^d	M12, M13, M21, I1, Z	Any other agreed composition											

^a Single values are maximum values.
^b "No requirement for analysis" is indicated by a dash.
^c For alloys intended for high temperature, Bi should be restricted to 20 ppm maximum.
^d Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and it is possible that two electrodes with the same Z classification are not interchangeable.

Table 1B — -4 — Symbols and all-weld metal chemical composition requirements of cored products for gas tungsten arc welding
(classification according to alloy type)

Alloy designation according to alloy type	Typical shielding gas (see 5.5)	Chemical composition, % (by mass) ^{a,b}											
		C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Others ^c
308L	11, Z	0,03	0,5 to 2,5	1,2	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	—	0,75	—	—
309L	11, Z	0,03	0,5 to 2,5	1,2	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,75	—	0,75	—	—
316L	11, Z	0,03	0,5 to 2,5	1,2	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	—	0,75	—	—
347	11, Z	0,08	0,5 to 2,5	1,2	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,75	8 × C to 1,0	0,75	—	—
Z ^d	11, Z	Any other agreed composition											
<p>^a Single values are maximum values.</p> <p>^b "No requirement for analysis" is indicated by a dash.</p> <p>^c For alloys intended for high temperature, Bi should be restricted to 20 ppm maximum.</p> <p>^d Consumables for which the chemical composition is not listed shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and it is possible that two rods with the same Z classification are not interchangeable.</p>													

Table 2A — Tensile properties of all-weld metal (classification according to nominal composition)

Alloy designation according to nominal composition	Minimum proof strength $R_{p0,2}$ MPa	Minimum tensile strength R_m MPa	Minimum elongation ^a %	Post-weld heat treatment
13	250	450	15	b
13 Ti	250	450	15	b
13 4	500	750	15	c
16 8 2	320	510	25	None
17	300	450	15	d
19 9 L	320	510	30	None
19 9 Nb	350	550	25	
19 12 3 L	320	510	25	
19 12 3 Nb	350	550	25	
19 13 4 N L	350	550	25	
19 9 H	350	550	30	
22 9 3 N L	450	550	20	
18 16 5 N L	300	480	25	
18 8 Mn	350	500	25	
18 9 Mn Mo	350	500	25	
20 10 3	400	620	20	
20 25 5 Cu N L	320	510	25	
21 10 N	350	550	30	
23 7 N L	450	570	20	
23 12 L	320	510	25	
23 12 Nb	350	550	25	
23 12 2 L	350	550	25	
29 9	450	650	15	
22 12 H	350	550	25	
25 20	350	550	20	
25 4	450	650	15	
25 9 4 Cu N L	550	620	18	
25 9 4 N L	550	620	18	
Z	Not specified			

^a Gauge length is equal to five times the test specimen diameter.

^b The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 840 °C and 870 °C, held for 2 h, then furnace cooled to 600 °C, then cooled in air.

^c The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 580 °C and 620 °C, held for 2 h, then cooled in air.

^d The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 760 °C and 790 °C, held for 2 h, then furnace cooled to 600 °C, then cooled in air.

Table 2B — Tensile properties of all-weld metal (classification according to alloy type)

Alloy designation according to alloy type	Minimum tensile strength MPa	Minimum elongation ^a %	Post-weld heat treatment	
307	590	25	None	
308	550	25		
308L	520	25		
308H	550	25		
308Mo	550	25		
308LMo	520	25		
308HMo	550	25		
308N	690	20		
309	550	25		
309L	520	25		
309H	550	25		
309Mo	550	15		
309LMo	520	15		
309LNiMo	520	15		
309LNb	520	25		
310	550	25		
312	660	15		
316	520	25		
316L	485	25		
316H	520	25		
316LCu	485	25		
317	550	20		
317L	520	18		
318	520	20		
347	520	25		
347L	520	25		
347H	520	25		
409	450	14		
409Nb	450	14		b
410	520	15		b
410NiMo	760	10		c
430	450	15		d
430Nb	450	12		d

Table 2B (continued)

Alloy designation according to alloy type	Minimum tensile strength MPa	Minimum elongation ^a %	Post-weld heat treatment
16-8-2	520	25	None
2209	690	15	
2307	690	18	
2553	760	13	
2594	760	13	
2594W	690	15	
Z	Not specified		

^a Gauge length is equal to five times the test specimen diameter.

^b The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 730 °C and 760 °C, held for 1 h, then furnace cooled to 315 °C, then cooled in air.

^c The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 590 °C and 620 °C, held for 1 h, then cooled in air.

^d The weld test assembly (or the blank from it, from which the tensile test specimen is to be machined) shall be heated to a temperature between 760 °C and 790 °C, held for 2 h, then furnace cooled to 600 °C, then cooled in air.

5.4 Symbol for type of core

The symbols in Table 3A and Table 3B indicate different types of tubular cored electrodes and rods relative to their core composition and slag characteristics.

Table 3A — Symbol for type of core
(classification according to nominal composition)

Symbol	Characteristics
B	Basic slag
R	Rutile, slow freezing slag
P	Rutile, fast freezing slag
M	Metal powder
U	Self-shielding
Z	Other types
See Annex B.	

Table 3B — Symbol for type of tubular cored electrode and rod (classification according to alloy type)

Symbol	Characteristics
F	Flux cored electrodes
M	Metal cored electrodes
R	Cored rods for gas tungsten arc welding
See Annex C.	

5.5 Symbol for shielding gas

The symbols for shielding gases shall be the classification of the gas in accordance with ISO 14175, except that the symbol NO shall be used for non-gas shielded tubular cored electrodes

5.6 Symbol for welding position

The symbols in Table 4A and Table 4B indicate the welding positions for which the product is suitable.

**Table 4A — Symbol for welding position
(classification according to
nominal composition)**

Symbol	Welding positions in accordance with ISO 6947
1	PA, PB, PC, PD, PE, PF and PG
2	PA, PB, PC, PD, PE and PF
3	PA and PB
4	PA
5	PA, PB and PG
PA = Flat position PB = Horizontal-vertical position PC = Horizontal position PD = Horizontal overhead position PE = Overhead position PF = Vertical up position PG = Vertical down position	

**Table 4B — Symbol for welding position
(classification according to alloy type)**

Symbol	Welding positions in accordance with ISO 6947
0	PA and PB
1	PA, PB, PC, PD, PE, PF or PG, or PF and PG
PA = Flat position PB = Horizontal-vertical position PC = Horizontal position PD = Horizontal overhead position PE = Overhead position PF = Vertical up position PG = Vertical down position	

6 Mechanical test

6A Classification according to nominal composition

Tensile tests and any required retests for tubular cored electrodes shall be carried out on weld metal in the condition specified in [Table 2A](#) (as-welded or post-weld heat treated) using an all-weld metal test piece in accordance with ISO 15792-1 of a type specified in [Table 6](#) using 1,2 mm, or, if this diameter is not manufactured, the next larger diameter manufactured as specified in [6.1](#) and [6.2](#).

Tensile tests for tubular cored rods shall be carried out on weld metal in the condition specified in [Table 2A](#) using an all-weld metal test piece in accordance with ISO 15792-1 of a type specified in [Table 6](#) using 2,0 mm, or, if this diameter is not manufactured, the next larger diameter manufactured as specified in [6.1](#) and [6.2](#).

6.1 Preheating and interpass temperatures

Preheating and interpass temperatures shall be selected for the appropriate weld metal type from [Table 5A](#) or [Table 5B](#).

The preheating and interpass temperatures shall be measured using temperature indicator crayons, surface thermometers or thermocouples in accordance with ISO 13916.

6B Classification according to alloy type

Tensile tests for tubular cored electrodes shall be carried out on weld metal in the condition specified in [Table 2B](#) (as-welded or post-weld heat treated) using an all-weld metal test piece in accordance with ISO 15792-1 of a type specified in [Table 6](#) using 1,2 mm, or, if this diameter is not manufactured, the next larger diameter manufactured as specified in [6.1](#) and [6.2](#).

Tensile tests for tubular cored rods shall be carried out on weld metal in the condition specified in [Table 2B](#) using an all-weld metal test piece in accordance with ISO 15792-1 of a type specified in [Table 6](#) using 2,2 mm, or, if this diameter is not manufactured, the next larger diameter manufactured as specified in [6.1](#) and [6.2](#).

The interpass temperature shall not exceed the maximum temperature indicated in Table 5A or Table 5B. If, after any pass, the interpass temperature is exceeded, the test assembly shall be cooled in air to a temperature within the limits of the interpass temperature.

Table 5A — Preheating and interpass temperatures (classification according to nominal composition)

Alloy designation according to nominal composition	Preheating and interpass temperatures °C
13 13Ti 17	200 to 300
13 4	100 to 180
All others	≤150

Table 5B — Preheating and interpass temperatures (classification according to alloy type)

Alloy designation according to alloy type	Preheating and interpass temperatures °C
410	200 to 300
409 409Nb 430 430Nb	150 to 260
410NiMo	100 to 260
All others	≤150

6.2 Pass sequence

The total number of runs, the number of runs per layer and the total number of layers shall be as given in [Table 6](#).

Table 6 — Pass sequence

Process	Diameter mm	ISO 15792-1 test piece type	Passes per layer		Total number of layers
			First layer	Other layers	
Gas shielded and non-gas shielded metal arc welding	<1,2	1.0	1 or 2	2 or 3 ^a	6 to 9
	1,2	1.3	1 or 2	2 or 3 ^a	5 to 9
	1,4 1,6 2,0	1.3	1 or 2	2 or 3 ^a	5 to 8
	2,4 3,2	1.3	1 or 2	1 or 2 ^b	4 to 7
Gas tungsten arc welding	2,0 2,2 2,4	1.0	1 or 2	2 or 3 ^a	5 to 8

^a Final layer may have four passes.
^b Final layer may have three passes.

7 Chemical analysis

Chemical analysis shall be performed on any specimen appropriate for the analytical method to be used. In case of dispute, specimens in accordance with ISO 6847 shall be used. Any analytical technique can be used, but in cases of dispute, reference shall be made to established published methods.

8 Rounding procedure

Actual test values obtained shall be subject to ISO 80000-1:2009, B.3, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this document, the measured values shall be converted to the units of this document before rounding. If an average value is to be compared with the requirements of this document, rounding shall be done only after calculating the average. The rounded results shall fulfil the requirements of the appropriate table for the classification under test.

9 Retests

If any test fails to meet the requirement(s), that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original test assembly or sample or from one or two new test assemblies. For chemical analysis, retests need only be for those specific elements that failed to meet the requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this document for that classification.

In the event that during preparation, or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the weld test assembly or sample(s) or test specimen(s), or in conducting the tests, the test shall be considered invalid. This determination is made without regard to whether the test was actually completed, or whether the test results met, or failed to meet, the requirements. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

10 Technical delivery conditions

Technical delivery conditions shall be in accordance with ISO 544 and ISO 14344.

11 Examples of designation

The designation of tubular cored product shall follow the principles given in the examples below.

11A Classification according to nominal composition

EXAMPLE 1A

A tubular cored electrode (T) for gas shielded arc welding deposits a weld metal of chemical composition within the limits for the nominal composition 19 12 3 L of [Table 1A](#).

The electrode with a rutile type core with a slow freezing slag (R) was tested under mixed gas (M21) and can be used in flat and horizontal-vertical positions (3).

This is designated as follows:

ISO 17633-A - T 19 12 3 L R M21 3

where

ISO 17633-A	is the number of this document with classification according to nominal composition;
T	indicates a tubular cored electrode for metal arc welding (see 5.2A);
19 12 3 L	represents the chemical composition of the all-weld metal (see Table 1A);

11B Classification according to alloy type

EXAMPLE 1B

A tubular cored electrode (TS) for gas shielded arc welding deposits a weld metal of chemical composition within the limits for the alloy type 316L of [Table 1B-1](#).

The flux cored electrode type (F) was tested under mixed gas (M21) and can be used in flat and horizontal-vertical positions (0).

This is designated as follows:

ISO 17633-B - TS 316L-F M21 0

where

ISO 17633-B	is the number of this document with classification according to alloy type;
TS	indicates a tubular cored stainless steel electrode for metal arc welding (see 5.2B);
316L	represents the chemical composition of the all-weld metal (see Tables 1B-1);

R	is the type of electrode core (see Table 3A);	F	is the type of tubular cored electrode (see Table 3B);
M21	is the shielding gas (see 5.5);	M21	is the shielding gas (see 5.5);
3	is the welding position (see Table 4A).	0	is the welding position (see Table 4B).

EXAMPLE 2A

A tubular cored electrode (T) for gas shielded arc welding deposits a weld metal of chemical composition within the limits for the nominal composition 19 12 3 L of Table 1A.

The electrode with a rutile type core with a slow freezing slag (R) was tested under mixed gas (M21) and can be used in flat and horizontal-vertical positions (3).

This is designated as follows:

ISO 17633-A - T Z 22 10 N H R C1 3

where

ISO 17633-A	is the number of this document with classification according to nominal composition;
T	indicates a tubular cored electrode for metal arc welding (see 5.1A);
Z	indicates that no chemical composition limits are specified (see Table 1A);
22 10 N H	represents the typical chemical composition of the all-weld metal with 22 % Cr, 10 % Ni, 0,1 % N and 0,05 % C;
R	is the type of electrode core (see Table 3A);
C1	is the shielding gas (see 5.5);
3	is the welding position (see Table 4A).

Annex A (informative)

Comparison charts of alloy designation according to nominal composition and alloy type

See Table A.1A and Table A.1B.

Table A.1A — Correspondence of alloy, designated according to nominal composition, with alloy, designated according to alloy type, of similar, but not identical, requirements

Nominal composition	Alloy type ^a
13	410
13 Ti	409
13 4	410NiMo
16 8 2	16-8-2
17	430
19 9 L	308L
19 9 Nb	347
19 12 3 L	316L
19 12 3 Nb	318
19 13 4 N L	—
19 9 H	308H
22 9 3 N L	2209
18 16 5 N L	—
18 8 Mn	—
18 9 Mn Mo	—
20 10 3	308Mo
20 25 5 Cu N L	—
21 10 N	—
23 7 N L	2307
23 12 L	309L
23 12 Nb	309Nb
23 12 2 L	309LMo
29 9	312

Table A.1B — Correspondence of alloy, designated according to alloy type, with alloy, designated according to nominal composition, of similar, but not identical, requirements

Alloy type	Nominal composition ^a
307	—
308	—
308L	19 9 L
308H	19 9H
308Mo	20 10 3
308LMo	—
308HMo	—
309	—
309L	23 12 L
309H	22 12 H
309Mo	—
309LMo	23 12 2 L
309LNb	—
310	25 20
312	29 9
316	—
316L	19 12 3 L
316H	—
316LCu	—
317	—
317L	—
318	19 12 3 Nb
347	19 9 Nb

Table A1.A (continued)

Nominal composition	Alloy type ^a
22 12 H	309H
25 20	310
25 4	—
25 9 4 N L and 25 9 4 Cu L	2594
^a “No correspondence of alloy designation in the classification according to alloy type” is indicated by a dash.	

Table A1.B (continued)

Alloy type	Nominal composition ^a
347L	—
347H	19 9 Nb
409	13 Ti
409Nb	—
410	13
410NiMo	13 4
430	17
430Nb	—
16-8-2	16 8 2
2209	22 9 3 N L
2307	23 7 N L
2553	25 9 4 Cu N L
2594	25 9 4 N L and 25 9 4 Cu L
^a “No correspondence of alloy designation in the classification according to nominal composition” is indicated by a dash.	

Annex B

(informative)

Description of types of core — Classification according to nominal composition

B.1 Symbol B in Table 3A

Tubular cored electrodes of the B type are characterized by a coarse droplet metal transfer and a slightly convex fillet weld. These tubular cored electrodes are primarily used with argon and carbon dioxide shielding gas mixtures in the flat and horizontal-vertical positions. The slag consists mainly of fluorides and oxides of alkaline earth metals. Welds with high impact resistance and low sensitivity for cracks are deposited.

B.2 Symbol R in Table 3A

Tubular cored electrodes of the R type are characterized by a spray metal transfer, low spatter loss, and a rutile-based slag that fully covers the weld bead. These tubular cored electrodes are designed for single and multiple pass welding in the flat and horizontal-vertical position. Tubular cored electrodes of the R type may be welded using carbon dioxide or mixed gases. However, the use of argon and carbon dioxide mixtures, when recommended by the manufacturer, can be used to improve arc transfer and reduce spatter.

B.3 Symbol P in Table 3A

Tubular cored electrodes of the P type are similar to the R type, but the rutile-based slag is designed for fast-freezing characteristics that enable welding in all positions. These tubular cored electrodes are generally produced in smaller diameters and exhibit spray metal transfer when using carbon dioxide or mixed gases for shielding. The running characteristics can be improved with the use of argon and carbon dioxide mixtures when recommended by the manufacturer.

B.4 Symbol M in Table 3A

Tubular cored electrodes of the M type are characterized by a droplet spray metal transfer and noticeably incomplete slag coverage. The core composition of these tubular cored electrodes consists of metal alloys and iron powder along with other arc enhancers which enable these tubular cored electrodes to produce high recovery rates with an insensitivity to lack of fusion. These tubular cored electrodes are primarily used with argon and carbon dioxide shielding gas mixtures in the flat and horizontal-vertical positions; however, welds in other positions are also possible using the short-circuiting or pulsed arc modes of transfer.

B.5 Symbol U in Table 3A

Tubular cored electrodes of the U type are used without a gas shield for single and multiple pass welding in the flat and horizontal-vertical welding positions. With some tubular cored electrodes, vertical down welding is possible.

B.6 Symbol Z in Table 3A

Tubular cored electrodes of the Z type are other types not covered by the descriptions in B.1 to B.5.

Annex C

(informative)

Description of types of tubular cored electrodes and rods — Classification according to alloy type

C.1 Flux cored electrodes (symbol F in Table 3B)

Flux cored electrodes show the suitable amount of slag generation for complete or nearly complete slag cover and the core contains both metallic and non-metallic ingredients.

C.2 Metal cored electrodes (symbol M in Table 3B)

Metal cored electrodes show a small amount of slag generation with minimal slag cover and the core contains metallic and minimum amount of non-metallic ingredients.

C.3 Cored rods for gas tungsten arc welding (symbol R in Table 3B)

Cored rods are used primarily for root pass welding of stainless steel piping joints when an inert gas backing purge is either not possible or not desirable. This rod can only be used with the gas tungsten arc welding process, but caution is advised as it produces a slag cover that requires removal before additional weld layers can be deposited.

Annex D (informative)

Considerations on weld metal ferrite contents

D.1 General

See Reference [3].

The ferrite content in stainless steel weld metals plays an important role in determining the fabrication and service performance of a welded construction. To prevent problems, a certain ferrite level is often specified. Originally, ferrite level was described in terms of ferrite percentage (by volume), but currently the Ferrite Number (FN) concept is used as specified in ISO 8249.

D.2 Effects of ferrite

The most important beneficial effect of ferrite in nominally austenitic stainless steel weldments is the well-established relationship between a reduced sensitivity to hot cracking and the presence of a certain amount of ferrite. The minimum ferrite limit necessary to ensure freedom from cracking depends, among other factors, on the weld metal composition. The upper limit results from possible impairment of either mechanical or corrosion properties, or both. The required amount of ferrite can be obtained by adjusting the ratio of ferrite promoters (such as chromium) to austenite promoters (such as nickel) within the limits allowed by the applicable specification.

D.3 Relation between composition and structure

As discussed in the following, ferrite is normally measured by means of magnetic instruments and stated in terms of FN. Ferrite can also be estimated by means of constitution diagrams. The most accurate version recommended is the WRC-1992 constitution diagram^[4] developed by the Welding Research Council (WRC). The composition is related to the structure through grouping the elements which promote ferrite in the so-called "chromium equivalent" and elements which promote austenite in the "nickel equivalent". By using Reference [4], the structure can be predicted with an accuracy of approximately ± 4 FN ferrite at a calculated level of up to 18 FN. It can be used for FN up to 100 (i.e. it can be used for duplex alloys).

D.4 Ferrite formation

It is generally agreed that hot cracking is governed by the solidification mode. The final ferrite content and morphology result from reactions during solidification and subsequently in the solid state. The hot cracking sensitivity decreases in the following order of solidification mode:

- a) single-phase austenitic;
- b) primary austenitic;
- c) mixed-type and single phase ferritic;
- d) primary ferritic.

Although both Ferrite Number and solidification mode depend mainly on composition, the relationship is not always unambiguous. However, the system is standardized and it is more practical to specify and to measure ferrite on this basis.

D.5 Effects of welding conditions

The ferrite content of weld metal is not determined solely by the filler metal selected. Apart from the effects of dilution from the base material, the ferrite content can be significantly affected by the welding conditions. Several factors can change the chemical composition of the weld metal. The most important of these is nitrogen, which can enter the weld metal through the welding arc. A high arc voltage, or a disturbance in the shielding gas flow, can result in a significantly decreased FN. Another factor is the reduction of chromium by oxidizing materials in the shield gas or the increase of carbon from carbon dioxide. Very high heat input can also have an effect, especially with duplex steels. When the ferrite content in undiluted weld metal is found to be significantly different from that quoted in the manufacturer's certification, one or more of the above factors are most likely to be the cause of the difference.

D.6 Effects of heat treatment

Stainless steel base metals are generally supplied in the solution annealed and quenched condition. In contrast, most welded joints are put into service in the as-welded condition. In some cases, however, a post-weld heat treatment can, or should, be applied. This can reduce the magnetically determined FN to some extent, even to zero. The effects of heat treatment on mechanical and corrosion properties can be significant, but are beyond the scope of this annex.

D.7 Determination of ferrite content

D.7.1 The several parties concerned with the integrity of a stainless steel weldment should all be able to agree upon the ferrite content. These parties could include the manufacturer of the filler material, the fabricator of the weldment, a code or regulatory body, and an insurance company. It is therefore essential that the method for the determination of ferrite be reproducible. Early observations of ferrite in stainless steel weld metals were largely by metallography. Etchants that darkened ferrite but left austenite untouched were used to estimate the percentage (by volume) of ferrite present. Unfortunately, the ferrite phase is extremely fine and very irregular in shape and is also not uniformly distributed in the matrix. The reliability and reproducibility of this method of estimation was poor. In addition, metallographic examination is a destructive test, which is not suitable for in-process quality assurance monitoring.

D.7.2 As ferrite is ferromagnetic, it is easily distinguishable from austenite. The magnetic response of an otherwise austenitic weld metal is approximately proportional to the amount of ferrite present. (The magnetic response is also affected by the composition of the ferrite — a more highly alloyed ferrite has a smaller magnetic response than an equivalent amount of lower alloyed ferrite.) This property can therefore be used for ferrite determination if it is possible to establish a calibration procedure for magnetic instruments. Of course, it would be desirable to establish a magnetic calibration procedure in such a fashion that the results are directly convertible into "per cent ferrite". However, because of the composition effect noted above, and because agreement on the true "per cent ferrite" proved to be impossible to achieve, an arbitrary "Ferrite Number" scale was adopted. The FN was initially believed to be a reasonable approximation of the "per cent ferrite" in a type 19 9 or type 308 weld metal, but later studies indicate that the FN appreciably overstates the "per cent ferrite" in a weld metal. From a practical standpoint, this is unimportant. Of much greater import is the ability of numerous measuring agencies to reproduce the same value for ferrite content within a small scatter band on a given weldment, and this the FN measurement system accomplishes.

D.7.3 In the FN system, calibration of certain laboratory instruments is established using, as primary standards, coating thickness standards¹⁾ consisting of a non-magnetic coating over a carbon steel substrate. To each coating thickness standard, an FN is assigned in accordance with ISO 8249:2000, Table 1. Further, in the FN system, instruments calibrated by primary standards can be used to assign FNs

1) Available from the US National Institute for Standards and Technology (NIST). This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the supplier named. Equivalent suppliers may be used if their products can be shown to lead to the same results.

to weld metal samples which can in turn be used as secondary standards for the calibration of numerous other instruments more suitable for a shop or field environment.

D.7.4 Using either primary or secondary calibration, round robin tests have established that the reproducibility of FN determination on given samples of weld metal is within ± 1 FN or less over the range 0 FN to 28 FN provided in ISO 8249. This is far better reproducibility than could be achieved using metallographic measurements. Principles for the extension of the system to ferrite levels appropriate to duplex steels have been established and this extension is specified in ISO 8249. Secondary standards are also now available¹⁾²⁾.

D.8 Implementation of FN measurement

For both specification and determination of ferrite, it is important to be realistic about what can be expected in a weldment. It is not realistic to specify, and expect to measure, 0 FN in nominally fully austenitic weld metal. Specification of 0,5 FN maximum is realistic and achievable. It is not realistic to specify, and expect to measure, an FN within a range that approaches the reproducibility of the welding operation and of measurement. Thus, specification of 5 FN to 10 FN, or 40 FN to 70 FN, is realistic and achievable. However, specification of 5 FN to 6 FN is not realistic, nor is specification of 45 FN to 55 FN.

It is not realistic to specify, and expect to measure, a narrow FN range for all points in a weld deposit because reheating of the overlap areas between passes constitutes a heat treatment and generally reduces the local ferrite content. It is not realistic to specify, and expect to measure, the same FN range on curved surfaces, surfaces very close to edges or to strongly magnetic materials, or on rough surfaces (including those containing the ripples of a normal weld deposit surface), as would be measured along the centreline of a weld run that is properly prepared smooth and flat after welding.

2) Secondary standards were formerly available from The Welding Institute, UK.

Bibliography

- [1] ISO 8249:2000, *Welding — Determination of Ferrite Number (FN) in austenitic and duplex ferritic-austenitic Cr-Ni stainless steel weld metals*
- [2] EN 12073:1999³⁾, *Welding consumables — Tubular cored electrodes for metal arc welding with or without a gas shield of stainless and heat-resisting steels — Classification*
- [3] LEFEBVRE J. Guidance on specifications of ferrite in stainless steel weld metal. *Weld. World*. 1993, 31 (6) pp. 390–406
- [4] KOTECKI D.J., & SIEWERT T.A. WRC-1992 constitution diagram for stainless steel weld metals: A modification of the WRC-1988 diagram. *Weld. J.* 1992, 71 (5) pp. 171s–178s

3) Superseded by this document.